



US010707531B1

(12) **United States Patent**
Harrup et al.

(10) **Patent No.:** **US 10,707,531 B1**
(45) **Date of Patent:** ***Jul. 7, 2020**

(54) **ALL-INORGANIC SOLVENTS FOR ELECTROLYTES**

(71) Applicants: **Mason K. Harrup**, Idaho Falls, ID (US); **Jay Fraser**, San Antonio, TX (US)

(72) Inventors: **Mason K. Harrup**, Idaho Falls, ID (US); **Jay Fraser**, San Antonio, TX (US)

(73) Assignee: **New Dominion Enterprises Inc.**, Austin, TX (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 177 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **15/717,474**

(22) Filed: **Sep. 27, 2017**

Related U.S. Application Data

(60) Provisional application No. 62/400,586, filed on Sep. 27, 2016.

(51) **Int. Cl.**
H01M 10/0569 (2010.01)
H01M 10/0525 (2010.01)
H01M 10/0568 (2010.01)
C07F 9/659 (2006.01)
H01M 10/0567 (2010.01)

(52) **U.S. Cl.**
CPC **H01M 10/0569** (2013.01); **C07F 9/659** (2013.01); **H01M 10/0525** (2013.01); **H01M 10/0567** (2013.01); **H01M 10/0568** (2013.01); **H01M 2300/0037** (2013.01)

(58) **Field of Classification Search**

CPC H01M 10/0569; H01M 10/0568; H01M 10/0567; H01M 10/0525; H01M 2300/0037; C07F 9/659

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,126,483 A	11/1978	Donakowski et al.
4,157,941 A	6/1979	Donakowski et al.
4,159,229 A	6/1979	Donakowski et al.
4,223,080 A	9/1980	Auborn
4,248,868 A	2/1981	Scartazzini et al.
4,270,957 A	6/1981	Donakowski et al.
4,483,908 A	11/1984	Zimmerman
4,613,676 A	9/1986	Fuhrer et al.
4,719,288 A	1/1988	Fuhrer et al.
4,722,877 A	2/1988	Sammells
4,727,060 A	2/1988	Buhlmyer et al.

(Continued)

FOREIGN PATENT DOCUMENTS

WO WO2013032004 3/2013

Primary Examiner — Laura Weiner

(74) *Attorney, Agent, or Firm* — Tully Rinckey PLLC; Steven M. Hoffberg

(57) **ABSTRACT**

An all-inorganic electrolyte formulation for use in a lithium ion battery system comprising at least one of each a phosphoranimine, a phosphazene, a monomeric organophosphate and a supporting lithium salt. The electrolyte preferably has a melting point below 0° C., and a vapor pressure of combustible components at 60.6° C. sufficiently low to not produce a combustible mixture in air, e.g., less than 40 mmHg at 30° C. A solid electrolyte interface layer formed by the electrolyte with an electrode is preferably thermally stable ≥80° C.

10 Claims, 2 Drawing Sheets

